

# **Kuwait Chemical Manufacturing Company KSC**

الشركّة ألكويتية للتصنيع الكيماوي (ش.م.ك.)

### TECHNICAL DATA SHEET

11 October 2011

LONG OIL ALKYD

KULAC LSN 51W/70

Kulac LSN 51W/70 is a 70% solids long oil alkyd in white spirits. Kulac LSN 51W/70 has been formulated for use in quality architectural coatings exhibiting good gloss, durability and yellowing resistance.

Kulac LSN 51W/70 was formerly manufactured and sold under the code of Kulac LOS 70WG.

## **Application Areas**

Kulac LSN 51W/70 may be used in the formulation of brush or roller applied decorative finishes such as:

- Enamels
- Undercoats
- Primers

Physical Characteristics			Compatibility Characteristics <sup>2</sup>	
Parameter	Units	Limits	Solvents	
Oil Length	%	± 57	Alcohols	Limited
Oil Type	Nil	Linoleic Rich	Aliphatics	Compatible
Non-Volatile Content	%	$70 \pm 2$	Aromatics	Compatible
Viscosity (25°C)	Poise	150 to 600	Esters	Compatible
Viscosity (25°C)	Gardner	$Z_6$ to $Z_8$	Ketones	Compatible
Viscosity (25°C) @ 55% solids	Gardner	W to X		
Solids @ 2 Poise in W.S.	%	± 47	Other Film Formers	
Acid Value (on solids)	mg KOH/g	10 Max.	Amino Resins	Incompatible
Colour	Gardner	5 Max.	Bodied Oils	Limited
Clarity	Nil	Clear	Chlorinated Rubber	Limited
B. K. Drying Times <sup>1</sup>			Drying Oils	Compatible
Touch Dry	Hours	± 2	Long Oil Alkyds	Compatible
Hard Dry	Hours	$\pm 3 \frac{1}{2}$	Medium Oil Alkyds	Compatible

### Note:

#### **Packaging**

Kulac LSN 51W/70 is available in 190 Kg Net mild steel tight head drums. For alternative packaging requirements please contact our Sales Department.

#### Variants

**Kulac LSN 51W/70** is currently not available in any variant forms.

### **Storage Stability and Safety**

Kulac alkyd resins should be stored below 30°C in a cool, dry position away from direct sunlight or other heat sources. Under these conditions the resins will have a shelf life of one year.

Kulac alkyds should additionally be stored and handled in accordance with local statutory regulations.

Address P. O. Box 26011, Safat, Kuwait, 13121 **Document Revision Number** 

(+965) 2326-3297 or 2326-3497

**Fax** (+965) 2326-0179

No warranty or guarantee, express or implied, is made regarding the performance or stability of any product since the manner of use and/or conditions of storage are beyond our control Additionally, KCMC are committed to improving all aspects of our product range through continued research and development. As such product composition and/or specifications may change without notice.

<sup>&</sup>lt;sup>1</sup> Sample containing 0.05% Co and 0.5% Pb on resin solids reduced to 100 seconds Ford 4 with white spirits and matured for 48 hours. The varnish is subsequently applied at a 75µ wet film thickness to glass panels and allowed to dry under laboratory conditions.

<sup>&</sup>lt;sup>2</sup> Compatibility characteristics are provided for guidelines only. Combinations should be thoroughly checked before use.